



# Technical Data

## Aptra<sup>®</sup> Classic

**Product Description:** High performance breathable PP film passes ASTM F 1671 - Viral Penetration and ASTM F 1670 Blood Borne Pathogen

Property	Test method	Unit	Average value	
Basis weight	ASTM D751	g/m <sup>2</sup>	25	
Embossed caliper	ASTM D751	µm	38	
Tensile strength	ASTM D751	N/inch	MD	18
			CD	16
Tensile elongation	ASTM D751	%	MD	120
			CD	75
MVTR	ASTM E96, method E	g/m <sup>2</sup> x24h	5000	

**US:**  
**RKW US, Inc.**  
Morris Collins  
3 Central Plaza / Box 347  
501 Broad Street / Suite 325  
Rome / Georgia 30161  
USA  
Telephone +1-706-232 3027  
Telefax +1-706-232 3084  
Email: [morris.collins@rkwus.com](mailto:morris.collins@rkwus.com)  
Web: [www.rkw-group.com](http://www.rkw-group.com)

**Europe:**  
**RKW SE**  
Robert Voggenauer  
Alkorstr. 6  
83512 Wasserburg am Inn  
Germany  
Phone +49-8071-72-279  
Fax +49-8071-596-762  
Email: [robert.voggenauer@rkw-group.com](mailto:robert.voggenauer@rkw-group.com)  
Web: [www.rkw-group.com](http://www.rkw-group.com)

The properties and values presented herein are to be considered only typical. No warranty or guarantee expressed or implied is made regarding the performance of the product, since the manner of use and handling is beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.

Edition 03/2005