



Technical Data

Aptra[®] UV 8

Product Description: High end UV stabilized breathable industrial PP film for outdoor applications

Property	Test method	Unit	Average value
Basis weight	ASTM D751	g/m ²	25
Embossed caliper	ASTM D751	µm	38
Tensile strength	ASTM D751	MD	18
		CD	16
Tensile elongation	ASTM D751	MD	120
		CD	75
MVTR	ASTM E96, method E	g/m ² x24h	5000

US:

RKW US, Inc.

Morris Collins

3 Central Plaza / Box 347
501 Broad Street / Suite 325
Rome / Georgia 30161
USA

Telephone +1-706-232 3027
Telefax +1-706-232 3084
Email: morris.collins@rkwus.com
Web: www.rkw-group.com

Europe:

RKW SE

Robert Voggenauer

Alkorstr. 6
83512 Wasserburg am Inn
Germany

Phone +49-8071-72-279
Fax +49-8071-596-762
Email: robert.voggenauer@rkw-group.com
Web: www.rkw-group.com

The properties and values presented herein are to be considered only typical. No warranty or guarantee expressed or implied is made regarding the performance of the product, since the manner of use and handling is beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.

Edition 01/2006